

<b>Low Flow Prepregs</b>	Epoxy type	<b>R-1661 L</b>
	Halogen-free Epoxy type	<b>R-1551 L</b>

Prepreg designation	Glass cloth Type	Resin content %	Calculated thickness $\mu\text{m}$
R-1661 LE	0,04 106	71	51
R-1661 L	0,06 1080	62	75
R-1661 LJ	0,06 1080	69	95
R-1661 LH	0,10 2116	55	132
Shelf life / expiration date		150 days at storage temperatures < 5°C 45 days at storage temperatures < 20°C	
R-1551 LE	0,04 106	73	52
R-1551 L	0,06 1080	63	73
R-1551 LJ	0,06 1080	71	97
R-1551 LH	0,10 2116	57	132
Shelf life / expiration date		120 days at storage temperatures < 5°C 30 days at storage temperatures < 20°C	



[ **Features** ]

- ▶ Greatly reduced possibility of resin flow
- ▶ Excellent low water absorption, copper foil peel strength and cost performance (Compared with glass-polyimide and polyimide adhesive).

[ **Applications** ]

Cellular phones (the hinge section, camera section and LCD section), digital camera, etc